

CASHMERE DEELITE

SOFT ORIGINS COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/8" cut pile Tufté 1/8" cut pile Getuftet 1/8" cut pile Getuft 1/8" cut pile	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PES	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Texflor back	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 E _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 1.210 gr/m²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 2.350 gr/m²		
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 8,3 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 10.8mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 67.200/m²		
PRODIS / GUT	TBC		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 21- LC5		



ITC CO BV
Kanegemstraat 15, B-8700 Tielt
itc-carpets.com

EN 14041
CE
25
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1011#IN00EL
Textile Floor Covering EN 1307
    
my.itc-carpets.com